



FERRO FRIT EUROPE

FERRO (HOLLAND) B.V.
CERAMIC DIVISION

P.O. Box 6088
3002 AB Rotterdam
van Helmontstraat 20
3029 AB Rotterdam
Tel. 010-47 84 911
Fax 010-47 77 526
Telex 22025 ferr nl
Cables: Fernam
Havennummer: 315

TECHNICAL DATA SHEET

PRODUKT: 12.95503.00 Cd/Se Glaze

TEMPERATURE: 1020 -1100 °C

CURVETIME:

COMPOSITION:

Li ₂ O	: 0.02	Al ₂ O ₃	: 0.19	SiO ₂	: 2.90
Na ₂ O	: 0.40	B ₂ O ₃	: 0.30	S	: 0.02
K ₂ O	: 0.01			Se	: 0.01
CaO	: 0.01			C	: 0.23
BaO	: 0.17				
PbO	: 0.06				
ZnO	: 0.27				
CdO	: 0.06				

CHARACTER. PHYS. PROP.:

Cubic Exp. 10^{-7} / °C : 204 (Calcul.)

Weakng. Tem. °C : 586 (Calcul.)

FINENESS : 1-2 % 250 mesh

R&D/CER

